

In the Specification:

Page 2, after line 22, please insert the following:

--The magnetic dispersion material is formed by a bulk material, a first and second colorant, a thickener and a magnetic material. In a preferred embodiment, the bulk material is liquid paraffin, the thickener is silica, and the magnetic material is iron powder. The colorants are titanium dioxide and benzo oxazole fluorescent whitener.--